

# TECHNICAL DATA SHEET

## TIPELIN 6000B

### HDPE for Blow moulding

TIPELIN / TIPOLEN / TIPPLEN / TATREN / BRALEN+

The joint product portfolio of MOL Petrochemicals and Slovnaft provides infinite opportunities

#### DESCRIPTION

**TIPELIN 6000B** is a high density bimodal polyethylene copolymer (with butene-1 as comonomer) intended for blow moulding of products with high stiffness and very good environmental stress crack resistance (ESCR). The grade contains antioxidant and acid scavenger.

#### APPLICATIONS

**TIPELIN 6000B** is recommended for thin walled, small bottles up to 5 litre capacity for consumer goods such as cosmetics, daily care etc. and for blow moulded products for packaging of aggressive industrial chemicals bounded to UN certificates. It is suitable for corrugated pipes too.

**TIPELIN 6000B** is suitable for food contact, for manufacturing of pharmaceutical packing products and toys. The product complies with Food Contact, Pharmaceutical and Toy Safety Regulations.

#### PROPERTIES

	Test method	Unit	Typical value
Melt Mass-Flow Rate (MFR) (190 °C /2.16 kg)	ISO 1133-1	g/10 min	0.30
Melt Mass-Flow Rate (MFR) (190 °C /5 kg)	ISO 1133-1	g/10 min	1.3
Melt Mass-Flow Rate (MFR) (190 °C /21.6 kg)	ISO 1133-1	g/10 min	30
Density (23 °C) *	ISO 1183-2	kg/m <sup>3</sup>	958
Tensile Strength at Yield *	ISO 527-3	MPa	32
Tensile Strain at Yield *	ISO 527-3	%	12
Tensile Strain at Break *	ISO 527-3	%	1400
Flexural modulus*	ISO 178	MPa	1800
Izod Impact Strength (notched, 23 °C)*	ISO 180/A	kJ/m <sup>2</sup>	9
Vicat Softening Temperature *	ISO 306/A 120	°C	127
Shore D Hardness *	ISO 868	-	65
ESCR F50 B (10% Igepal CO-630)*	ASTM D 1693	h	200
OIT (200 °C) *	EN 728	min	30

Typical properties, not to be used as specification.

\* Average mechanical property values of several measurements carried out on standard pressed specimens (ISO 293) conditioned at room temperature (ISO 291).

#### PROCESSING

**TIPELIN 6000B** can be used in conventional extrusion machines.

Recommended processing temperatures are 180-220°C.

# TECHNICAL DATA SHEET

## TIPELIN 6000B

### HDPE for Blow moulding

TIPELIN / TIPOLEN / TIPPLEN / TATREN / BRALEN+

The joint product portfolio of MOL Petrochemicals and Slovnaft provides infinite opportunities

2

## STORAGE AND HANDLING

Pellets are packed in 25 kg PE-LD bags and transported on stretch or shrink-wrapped pallets at eligible load of polymer 1375 kg. Heat treated pallets are available as well. We use adhesive between the bags in order to avoid their slipping. Pay attention to this fact during the removing of the bags from the pallets. The preferred method is to lift the bag at first without rotation. Transportation in a road silo or rail silo is also available. For more detailed information please contact SLOVNAFT and MOL Petrochemicals sales representative.

Since polyethylene is a combustible substance, the fire safety rules applicable for combustible materials in warehouses and store rooms should be observed.

If polymer is stored in conditions of high humidity and fluctuating temperatures, then atmospheric moisture can condense inside the packing. If it happened, it is recommended the pellets to be dried before use. During the storage polyethylene should not be exposed to UV radiation and temperatures above 40°C. Producer does not take responsibility for any damages caused by adverse storage.

## REACH STATEMENT

Polymers are exempt of REACH registration. However, their raw materials which mean monomers and relevant additives have been registered. MOL Petrochemicals is committed to fully respect legislation and will only use REACH compliant raw materials. At this point in time TIPELIN does not contain any substances specifically identified as SVHC at levels greater than 0.1%.

## SAFETY

See MSDS.

## RECYCLING

Polyethylene resins are suitable for recycling using modern recycling methods. In-house production waste should be kept clean to facilitate direct recycling.

## DISCLAIMER

The information provided in this publication has been compiled to the best of our present knowledge. However, in view of the various applications of polyethylene resins and the equipment used, the processing conditions may differ.

The recommendations and data herein are to be construed as informational only and do not relieve users from carrying out their own tests and experiments prior to processing in order to check suitability for a specific use. It is the responsibility of those to whom we supply our products to ensure that any proprietary rights and existing laws and legislation are observed. Our products are under continuous development, therefore we reserve the right to change the information presented in this brochure at our own discretion.

The REACH statement herein does not constitute legal advice. The REACH statement is provided for informational purpose only.

# TECHNICAL DATA SHEET

## TIPELIN 6000B

### HDPE for Blow moulding

TIPELIN / TIPOLEN / TIPPLEN / TATREN / BRALEN+

The joint product portfolio of MOL Petrochemicals and Slovnaft provides infinite opportunities

#### MANUFACTURER

##### **MOL Petrochemicals Co. Ltd.**

H-3581 Tiszaújváros,  
P.O. Box: 20  
Hungary

#### TECHNICAL SERVICE

##### **MOL Plc.**

##### **Polymer Technical Service MOL**

H-3581 Tiszaújváros,  
P.O. Box: 20  
Hungary

Telephone:  
+36 49 521 540  
+36 49 522 607  
Fax: +36 49 886 491

[E-mail: pts@mol.hu](mailto:pts@mol.hu)

#### SALES ORGANIZATION

##### **GERMANY**

Im Trutz Frankfurt 49, D-60322  
Frankfurt am Main, Germany  
Telephone: +49 69 154 04 0  
Fax: +49 69 154 04 41  
E-mail: polymersales@molgermany.de

##### **ITALY**

Via Teulié, 1,  
20136 Milano, Italy  
Telephone: +39 02 58 30 5523  
Fax: +39 02 58 30 3492  
E-mail: tvkitaly@it.tvk.eu

##### **POLAND**

Ul. Postępu 17D  
02-676 Warszawa, Poland  
Telephone: +48 22 545 70 70  
Fax: +48 22 545 70 60  
E-mail: petchem@slovnaft.pl

##### **AUSTRIA**

Walcherstrasse 11A, 7.Stock  
A- 1020 Wien, Austria  
Telephone: +43 1 211 20 1120  
Fax: +43 1 211 20 1198  
E-mail: JHauk@molaustria.at

##### **FRANCE**

Paris, France  
Mobile Phone: + 33 7 89 86 10 64  
Telephone: + 33 1 64 32 44 17  
E-mail: husson.iren@fr.tvk.eu

##### **ROMANIA**

Str. Danielopolu 4-6  
ET1 Sector 1 Cod 014 134  
Bucuresti, Romania  
Telephone:  
+40 21 204 85 00  
+40 21 204 85 02  
Fax: +40 21 232 10 59  
E-mail: petchem@molromania.ro

# TECHNICAL DATA SHEET

## TIPELIN 6000B

### HDPE for Blow moulding

TIPELIN / TIPOLEN / TIPPLEN / TATREN / BRALEN+

The joint product portfolio of MOL Petrochemicals and Slovnaft provides infinite opportunities

4

#### HUNGARY

H-3581 Tiszaújváros,  
P.O. Box: 20  
Hungary  
Telephone: +36 49 521 355  
Fax: +36 49 886 491  
E-mail: polymersales@mol.hu

#### UKRAINE

04655 Kiev  
Stepana Bandery ave., 23, 7th floor, of. 305,  
Ukraine  
Telephone:  
+380 44 374 00 80  
+380 67 463 58 69  
Fax: +380 44 374 00 90  
E-mail: JZavojko@mol-ukraine.com.ua

#### OTHER EUROPEAN COUNTRIES

Telephone:  
+36 49 521 355  
+36 70 458 4563  
+36 70 373 9209  
Fax: + 36 49 886 491  
E-mail: polymersales@mol.hu

#### SLOVAKIA AND CZECH REPUBLIC

Vlčie hrdlo 1  
824 12 Bratislava, Slovak Republic  
Telephone:  
+ 421 2 5859 7515  
+ 421 2 5859 7622  
+ 421 2 5859 7741  
+ 421 2 5859 7231  
E-mail: polymersales@slovnaft.sk

#### CROATIA, SLOVENIA, SERBIA, BOSNIA AND HERZEGOVINA, MONTENEGRO, ALBANIA, KOSOVO

Savska cesta 41/XIII  
HR-10000 Zagreb, Croatia  
Telephone: +385 1 6160 600  
Fax: +385 1 6160 601  
E-mail: polymersales@tifon.hr

June, 2017